



佳鉞有限公司 GOOPA LIMITED

香港青衣長達路 14-20 號, 偉力工業大廈 B 座 10/F 2 室
Room 2, Block B 10/F, Vigor Industrial Building,
14-20 Cheung Tat Road, Tsing Yi, N.T., Hong Kong
Tel: 24314718, 24971998/24972198 Fax: (852)24971826
<http://www.goopa.biz.com.hk> e-mail: info@goopa.com.hk



Dura-Tuff Clear Coat is a superior strength polyurethane coating that creates a tough, UV and scratch-resistant, clear-gloss finish. It is one of the easiest coatings to apply and provides many years of protection. FAMOWOOD Dura-Tuff is a quick-drying primer and an intermediate and finish coat all in one.

- **Easy:** With FAMOWOOD Dura-Tuff, there is nothing to add or mix. This clear gloss, moisture cure urethane replaces varnish is non-yellowing and maintains superior adhesion.
- **Outstanding UV protection:** FAMOWOOD Dura-Tuff is UV-resistant. Use over FAMOWOOD Glaze Coat.
- **Tough:** Designed for use on hardwood floors, floor boards, boats and other surfaces needing abrasion and scratch resistance.
- **Fast drying:** Dries in half the time varnishes require.

Use FAMOWOOD Dura-Tuff Clear Coat for:

- **Marine:** Protect above-water surface areas of canoes, fiberglass and wood boats, hydroplanes, and driftboats. Also protect floorboards, paddles, oars, seats, decks and walkways.
- **Home:** Hardwood floors, doors, exposed aggregate walk and driveways, wood garden furniture. Protect all types of metal, and ultra violet protection for clear epoxy resin surfaces. (Note: Dura-Tuff is slippery when wet. For walking or stepping surfaces, non-skid granules must be added.)
- **Sports:** Snow and water skis, fishing lures and poles, golf clubs, bows & arrows, gym floors-any sporting good where wear and tear on the coating is important.
- **Industrial:** Industrial floors, clear protection for all types of copper, bronze, ferrous metals and aluminum. (Aluminum should be treated with ALODINE™ prior to applying Dura-Tuff.)



佳鉞有限公司
GOOPA LIMITED

香港青衣長達路 14-20 號, 偉力工業大廈 B 座 10/F 2 室
Room 2, Block B 10/F, Vigor Industrial Building,
14-20 Cheung Tat Road, Tsing Yi, N.T., Hong Kong
Tel: 24314718, 24971998/24972198 Fax: (852)24971826
<http://www.goopa.biz.com.hk> e-mail: info@goopa.com.hk

Directions:

Please refer to the complete instructions and information for important details on LARGE AREA APPLICATIONS.)

Begin By Preparing the Surface

Always test a small area before use to ensure that FAMOWOOD Dura-Tuff is compatible.

Aluminum:

1. On new surface: Clean surface with commercial solution of phosphoric acid and rinse thoroughly with clean water. Use ALODINE™ 1201 Coating chemical, which produces a light gold to tan chemical conversion coating on aluminum, that provides corrosion resistance and paint adhesion.
2. On old surface: Remove all paint, grease or oil contaminants and clean surface as above.

Fiberglass:

1. Sand with medium grade production sandpaper until surface has a matte finish with no trace of gloss or sheen remaining.
2. After sanding, wipe with a clean cloth saturated with paint thinner.

Wood:

1. Remove all old paint and sand surface with course-grade production sandpaper.
2. Fill all abrasions, dents, cracks and holes with FAMOWOOD Wood Filler.
3. Sand with medium-grade to remove any scratches from previous sanding and blend in filled areas.
4. Finish sanding with fine-grain production sandpaper.
5. Remove all dirt and dust with a clean cloth saturated with paint thinner.



佳鉞有限公司 GOOPA LIMITED

香港青衣長達路 14-20 號, 偉力工業大廈 B 座 10/F 2 室
Room 2, Block B 10/F, Vigor Industrial Building,
14-20 Cheung Tat Road, Tsing Yi, N.T., Hong Kong
Tel: 24314718, 24971998/24972198 Fax: (852)24971826
<http://www.goopa.biz.com.hk> e-mail: info@goopa.com.hk

Applying To Surface

Follow these step-by-step directions when using FAMOWOOD Dura-Tuff Clear Coat:

1. Dura-Tuff clear coat is ready to use. No mixing or thinning required.
2. Maintain minimum 30% humidity in work area.
3. TEST SMALL AREA BEFORE FULL USE. Apply only on dry surfaces, as moisture will stop the curing process.
4. Remove all grease, wax, paint, paint remover and other contaminants.
5. Sand surface smooth and wipe clean with tack rag.
6. Brush or spray on in one direction following the Brushing or Spraying steps noted below.
7. If applied over existing paints or varnishes, check for compatibility, wrinkling, loss of adhesion, etc.
8. Always pour amount required for project into separate container. To prevent lip from sticking to container, wipe lid and rim clean and apply thin layer of paste wax to these surfaces
9. Under average (70°F) conditions, Dura-Tuff Clear Coat dries tack-free in 2 to 4 hours. If more than 8 hours has lapsed between coats, sand the previous coat.
10. Brushes or spray equipment may be cleaned in lacquer thinner. A light sanding between coats is recommended. Additional coats can be applied when surface is tack-free.
11. COVERAGE: Approximately 100 square feet per quart.

NOTE: Always apply in well-ventilated area. Do not thin Dura-Tuff. Wear gloves and appropriate skin protection.

Brushing:

1. Use natural bristle brush or a short bristle pad.
2. Apply in one direction (avoid back and forth motion).
3. Additional coats can be applied when surface is tack free.
4. A light sanding between coats is recommended.

Spraying:

1. An airless system is recommended with .011 to .013 nozzle size.
2. If using siphon cup arrangement with air compressor, all water filters must be in good working condition.
3. Air spray-siphon .070 nozzle and 10 to 12 cfm aircap.

For technical support, contact our Technical Service Department by mail, email, or phone. Our office hours are 7:30 A.M.-

4:00 P.M. (CST) Monday through Friday. Please [contact us](#) for more information. To request a Material Safety Data Sheet

(MSDS) please send an email to msds@eclecticproducts.com



佳鉞有限公司 GOOPA LIMITED

香港青衣長達路 14-20 號, 偉力工業大廈 B 座 10/F 2 室
Room 2, Block B 10/F, Vigor Industrial Building,
14-20 Cheung Tat Road, Tsing Yi, N.T., Hong Kong
Tel: 24314718, 24971998/24972198 Fax: (852)24971826
<http://www.goopa.biz.com.hk> e-mail: info@goopa.com.hk

Answers to Dura-Tuff Questions

What can FAMOWOOD Dura-Tuff Clear Coat be used on?

MARINE: Above-water areas of fiberglass and wood boats, hydroplanes, driftboards, canoes, oars, paddles, floorboard, seats, decks, walkways, and ultra violet protection for clear epoxy resin surfaces.

HOME: Hardwood floors, exposed aggregate walk and driveways, protect all types of metal, and ultra violet protection for clear epoxy resin surfaces.

SPORTS: Snow and water skis, fishing lures and poles, golf clubs, bows & arrows, gym floors. Any sporting good where wear and tear on the coating is important.

INDUSTRIAL: Industrial floors, clear protection for all types of copper, bronze, ferrous metals and aluminum. (Aluminum should be treated with ALODINE™ prior to applying Dura-Tuff.)

Is FAMOWOOD Dura-Tuff Clear Coat easy to use?

Yes. FAMOWOOD Dura-Tuff Clear Coat is one of the easiest coatings to apply and provides many years of protection.

How long does FAMOWOOD Dura-Tuff Clear Coat take to dry?

FAMOWOOD Dura-Tuff Clear Coat under average (70°F) conditions, dries tack-free in 2 to 4 hours. If more than 8 hours has lapsed between coats, sand the previous coat. FAMOWOOD® Dura-Tuff Clear Coat dries in 1/2 the time as varnishes.

What makes FAMOWOOD® Dura-Tuff Clear Coat unique?

- FAMOWOOD Dura-Tuff is a quick drying primer and an intermediate and finish coat all in one.
- With FAMOWOOD Dura-Tuff, there is nothing to add or mix. This clear gloss, moisture cure urethane replaces varnish and is non-yellowing and maintains superior adhesion.
- FAMOWOOD Dura-Tuff is UV resistant.
- FAMOWOOD Dura-Tuff is ideal for surfaces needing abrasion resistance.

Can FAMOWOOD Dura-Tuff Clear Coat be used to protect steps?

FAMOWOOD Dura-Tuff Clear Coat is slippery when wet. For walking or stepping surfaces, non-skid granules must be added.