

# Technical Data Sheet

## Benzoflex™ 2088 Plasticizer

### Applications

- Adhesives/sealants-b&c
- Flooring
- Vinyl plastisols

### Product Description

Benzoflex™ 2088 is a high solvating plasticizer known for its exceptional performance in PVC, polyvinyl acetate and water-based adhesive systems. In adhesives, it displays excellent wet tack, set times and open times and also improves adhesion in acrylic latex caulks. In PVC it serves as a fast fuser, delivering low processing temperatures and low volatility.

### Typical Properties

Property	Typical Value, Units
<b>General</b>	
Acidity (wt%)	0.1 max.
Color Pt-Co	25-40
Refractive Index @ 25°C	1.54
Specific Gravity @ 20°C/20°C	1.16
Boiling Point	673 °F (356 °C)
Flash Point Setaflash Closed Cup	396 °F (202 °C)
Freezing Point	<61 °F (<16 °C)
Vapor Pressure @ 20°C	<0.00001 torr (<0.0013 Pa)
Viscosity @ 25°C	71 cP (71 mPa·s)
Wt/Vol @ 20°C	9.68 lb/gal (1.16 kg/L)

### Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

*Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

