

Technical Data Sheet

Benzoflex™ 9-88 SG Plasticizer

Applications

- Adhesives/sealants-b&c
- Graphic arts
- Polyurethanes

Product Description

Benzoflex™ 9-88 SG is a non-phthalate plasticizer specifically designed for 2K polyurethane systems where it is very compatible and efficient.

Typical Properties

Property	Typical Value, Units
General	
Acidity (wt%)	0.1 max.
Color Pt-Co	120 max.
Refractive Index @ 25°C	1.52
Specific Gravity @ 20°C/20°C	1.12
Hydroxyl Number	6 max.
Boiling Point	657 °F (347 °C)
Flash Point Setaflash Closed Cup	360 °F (182 °C)
Freezing Point	-22 °F (-30 °C)
Vapor Pressure @ 20°C	<0.00001 torr (<0.0013 Pa)
Viscosity @ 25°C	105 cP (105 mPa·s)
Wt/Vol @ 20°C	9.35 lb/gal (1.12 kg/L)

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

© 2021 Eastman Chemical Company or its subsidiaries. All rights reserved. As used herein, ® denotes registered trademark status in the U.S. only.