

Technical Data Sheet

Benzoflex™ 50 Plasticizer

Applications

- Adhesives/sealants-b&c
- Flexible pvc compounds
- General industrial coatings
- Paints & coatings
- Vinyl plastisols

Product Description

Benzoflex™ primarily is known for its exceptional performance in polyvinyl acetate and water-based adhesives.

Typical Properties

Property	Typical Value, Units
General	
Acidity (wt%)	0.1 max.
Color Pt-Co	40-80
Refractive Index @ 25°C	1.53
Specific Gravity @ 20°C/20°C	1.15
Boiling Point	698 °F (370 °C)
Flash Point Setaflash Closed Cup	378 °F (192 °C)
Freezing Point	<61 °F (<16 °C)
Vapor Pressure @ 20°C	<0.00001 torr (<0.0013 Pa)
Viscosity @ 25°C	78 cP (78 mPa·s)
Wt/Vol @ 20°C	9.6 lb/gal (1.15 kg/L)

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

