

POKETONE® M33FM2A-WH1

Description

10% Mineral-reinforced grade
 Purpose: Food Contact, Outdoor
 Color: White

Physical Properties

	Value	Unit	Test Method & Condition
Density	1.35	g/cm ³	ASTM D792
Melt flow index 240°C/2.16kg	40	g/10min	ASTM D1238

Mechanical Properties

	Value	Unit	Test Method & Condition
Tensile strength at yield	50	MPa	ASTM D638
Tensile elongation at break	15	%	ASTM D638
Flexural strength	65	MPa	ASTM D790
Flexural modulus	2,300	MPa	ASTM D790
Notched Charpy impact strength	6	kJ/m ²	ISO 179/1eA, 23°C

Thermal Properties

	Value	Unit	Test Method & Condition
Melting temperature	222	°C	ASTM D3418

Injection Molding Processing Conditions

		Value	Unit
Pre-drying	Drying temperature	80	°C
	Drying time	3 ~ 4	hr
	Suggested max moisture	0.20	%
Temperature	Nozzle temperature	240	°C
	Zone 1 temperature	230	°C
	Zone 2 temperature	220	°C
	Zone 3 temperature	215	°C
	Zone 4 temperature	210	°C
	Processing temperature	235 ~ 250	°C
	Mold temperature	60 ~ 80	°C
Pressure	Back pressure	0.3 ~ 0.7	MPa
Speed	Screw Speed	50 ~ 100	rpm

All products purchased from or supplied by Hyosung Chemical Corporation are subject to terms and conditions set out in the contract, order acknowledgement and/or bill of loading. Hyosung Chemical warrants only that its product will meet those specifications designated as such herein or in other publications. All other information, including that herein, supplied by Hyosung Chemical is considered accurate but is furnished upon the express condition that the customer shall make its own assessment to determine the product's suitability for a particular purpose. Hyosung Chemical makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent. Any references in this brochure to "Hyosung Chemical" refer to the collectivity of Hyosung Chemical engaged in the manufacture and sale of chemical products. Particular contracts are entered into by any such company individually and any warranty, representation or any other commitment provided by Hyosung Chemical is the commitment of such individual company only.