

POKETONE® M630V

Description

General-purpose injection molding grade (UV reinforced)

| Physical Properties | ASTM | Value | ISO | Value |
|----------------------------------------|----------|------------------------|-------|------------------------|
| Density | D792 | 1.24 g/cm ³ | 1183 | 1.24 g/cm ³ |
| Shore D hardness | D2240 | | 868 | 76 |
| Hardness Rockwell | D785 | 110 | 2039 | |
| Water absorption equilibrium at RH 50% | D570 | 0.5 % | 62 | 0.5 % |
| Water absorption at Saturation | D570 | 2.1 % | 62 | 2.1 % |
| Melt flow index 240°C/2.16kg | D1238 | 6 g/10 min | 1133 | 5.6 ml/10 min |
| Mold Shrinkage | D955 | | 294-4 | |
| | MD, 3 mm | 2.1 % | | |
| | TD, 3 mm | 2.1 % | | |
| | MD, 2 mm | 1.6 % | | |
| | TD, 2 mm | 1.5 % | | |

| Mechanical Properties | ASTM | Value | ISO | Value |
|----------------------------------|--------|-----------|---------|----------------------|
| Tensile strength at yield | D638 | 58 MPa | 527-1 | 58 MPa |
| Tensile modulus | D638 | 1,450 MPa | 527-1 | 1,350 MPa |
| Tensile elongation at yield | D638 | 22 % | 527-1 | 22 % |
| Tensile elongation at break | D638 | ≥ 200 % | 527-1 | ≥ 200 % |
| Flexural strength | D790 | 53 MPa | 178 | 53 MPa |
| Flexural modulus | D790 | 1,350 MPa | 178 | 1,250 MPa |
| Unnotched Izod impact strength | D256 | N.B. | 180/1U | N.B. |
| Notched Izod impact strength | D256 | | 180/1A | |
| | 23 °C | 220 J/m | 23 °C | 15 kJ/m ² |
| | -10 °C | 65 J/m | -10 °C | 6 kJ/m ² |
| | -30 °C | 52 J/m | -30 °C | 4 kJ/m ² |
| Unnotched Charpy impact strength | D6110 | | 179/1eU | N.B. |
| Notched Charpy impact strength | D6110 | | 179/1eA | |
| | | | 23 °C | 17 kJ/m ² |
| | | | -10 °C | 4 kJ/m ² |
| | | | -30 °C | 3 kJ/m ² |
| Falling dart impact strength | | | 6603-2 | 50 J |
| | | | 23 °C | |

| Thermal Properties | ASTM | Value | ISO | Value |
|-----------------------------------------|-----------|----------------------|----------|--------|
| Melting temperature | D3418 | 222 °C | 11357 | 222 °C |
| Coefficient of linear thermal expansion | E831 | | 11359 | |
| | 25 ~ 55°C | 1.0×10 ⁻⁴ | | |
| Vicat softening point | D1525 | | 306/B50 | |
| | 5 kg | 192 °C | 50 N | 190 °C |
| Heat deflection temperature | D648 | | 75 | |
| | 66 psi | 195 °C | 0.45 MPa | 185 °C |
| | 264 psi | 102 °C | 1.8 MPa | 90 °C |

Wear & Abrasion Resistance

| | Pin on Disk | Thrust Washer |
|-----------------------------------------------|------------------------------|------------------------------|
| * Condition | 1.3 MPa, 0.06 m/sec | 0.4 MPa, 0.12 m/sec |
| Dynamic coefficient of Friction against self | 0.21 | 0.34 |
| Dynamic coefficient of Friction against steel | 0.36 | 0.60 |
| Wear factor against self | 0.0074 mm ³ /N·km | 0.0044 mm ³ /N·km |
| Wear factor against steel | 0.073 mm ³ /N·km | 0.04 mm ³ /N·km |
| Taber abrasion 1kg load, CS-17 wheel | ASTM D1044 | 12 mg/1,000 cycle |

Flammability Properties

| | Test Method & Condition | Value |
|------------------|-------------------------|-------------|
| Flame resistance | UL 94 | HB (0.8 mm) |

Electrical Properties

| | Test Method & Condition | Value |
|-----------------------------|-------------------------|-----------------------------------|
| Dielectric Strength (DS) | ASTM D149 3 mm | 15 kV/mm |
| | 2 mm | 19 kV/mm |
| Volume Resistivity (VR) | ASTM D257 | 10 ¹⁴ Ω·cm |
| Surface Resistivity (SR) | ASTM D257 | 10 ¹⁷ Ω/m ² |
| Dielectric constant at 60Hz | ASTM D150 | 6.1 |
| Dissipation factor at 60Hz | ASTM D150 | 0.009 |

Injection Molding Processing Conditions

| | Value | |
|-------------|------------------------|-------------------|
| Pre-drying | Drying temperature | 80 °C |
| | Drying time | 3 ~ 4 hr |
| | Suggested max moisture | 0.20 % |
| Temperature | Nozzle temperature | 250 °C |
| | Zone 1 temperature | 240 °C |
| | Zone 2 temperature | 230 °C |
| | Zone 3 temperature | 225 °C |
| | Zone 4 temperature | 220 °C |
| | Processing temperature | 235 ~ 250 °C |
| | Mold temperature | 60 ~ 80 °C |
| Pressure | Back pressure | 0.294 ~ 0.686 MPa |
| Speed | Screw Speed | 50 ~ 100 rpm |

* The data listed here is not for specification warranty, but typical value.

All products purchased from or supplied by Hyosung Chemical Corporation are subject to terms and conditions set out in the contract, order acknowledgement and/or bill of loading. Values given above are simply references for representing typical level and do not expressly or impliedly guarantee anything. Neither should it be interpreted as specification limit nor sole criterion for part/tool design that is intended to have a legal binding effect. All other information, including that herein, supplied by Hyosung Chemical is considered accurate but is furnished upon the express condition that the customer shall make its own assessment to determine the product's suitability for a particular purpose. Hyosung Chemical makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent. Any references in this brochure to "Hyosung Chemical" refer to the collectivity of Hyosung Chemical engaged in the manufacture and sale of chemical products. Particular contracts are entered into by any such company individually and any warranty, representation or any other commitment provided by Hyosung Chemical is the commitment of such individual company only.