

# PK JH960TF4U

## Description (简介)

PTFE enhanced low friction coefficient in flow.

PTFE增强 低摩擦系数 低磨损.

Physical Properties (物理性能)	Test Method	Unit (单位)	Value(数值)
Density密度	ASTM D792	g/cm3	1.31
Shore D hardness 邵氏硬度D	ASTM D2240	D	---
Hardness Rockwell 洛氏硬度R	ASTM D785	R	110
Water absorption equilibrium at RH 50% 50%湿度下的吸水率	ASTMD570	%	---
Water absorption at Saturation 饱和吸水率	ASTMD570	%	---
Melt flow index 240°C/2.16kg 熔指	ASTM D1238	240°C,2.16Kg	40
Mold Shrinkage 模具收缩率	D955		
	MD, 3 mm		1.5%
	TD, 3 mm		1.8%
	MD, 2 mm		1.6%
	TD, 2 mm		1.9%

Mechanical Properties (机械性能)	Test Method	Unit (单位)	Value(数值)
Tensile strength at yield 拉伸强度	ASTM D638	MPa	40
Tensile modulus 拉伸模量	ASTM D638	MPa	1300
Tensile elongation at break 断裂伸长率	ASTM D638	%	150
Flexural strength 弯曲强度	ASTM D790	MPa	45
Flexural modulus 弯曲模量	ASTM D790	MPa	1250
Cantilever beam notch impact 悬臂梁缺口冲击	ASTM D256	kJ/m2	13
		J/m	140

Thermal Properties (热学性能)	Test Method	Unit (单位)	Value(数值)
Melting temperature 熔点	D3418	°C	222
Coefficient of linear thermal expansion, 25 ~ 55°C 线性热膨胀系数 25 ~ 55°C	E831		
	TD	-	8.5×10 <sup>-5</sup>
	MD		4.6×10 <sup>-5</sup>
Vicat softening point 维卡软化点	D1525 5Kg	°C	195
Heat deflection temperature 热变形温度	D648		
	66 psi 0.45Mpa 26 psi 1.8Mpa	°C	200 105

Flammability Properties(燃烧特性)	Test Method (测试方法)	Value(数值)
Flame resistance 阻燃性	UL 94	HB
Glow Wire Ignition Temperature (GWIT) 灼热丝起燃温度	IEC 60695-2-13	----
Glow Wire Flammability Index (GWFI) 灼热丝可燃性指数	IEC 60695-2-12	----

Electrical Properties (电气性能)	Test Method	Value(数值)
Dielectric Strength (DS) 介电强度	ASTM D149 3 mm	---
	2 mm	
Volume Resistivity (VR) 体积电阻率	ASTM D257	---
Surface Resistivity (SR) 表面电阻率	ASTM D257	---
Dielectric constant at 60Hz 60Hz下的介电常数	ASTM D150	---
Dissipation factor at 60Hz 60Hz下的介电损耗	ASTM D150	---

Injection Molding Processing Conditions 注塑工艺指南		Value(数值)
Pre-drying 预干燥	Drying temperature 干燥温度	80 °C
	Drying time 干燥时间	3 ~ 4 hr
	Suggested max moisture 建议最大湿度	0.20 %
Temperature 温度	Nozzle temperature 喷嘴温度	240 °C
	Zone 1 temperature 第一段温度	230 °C
	Zone 2 temperature 第二段温度	220 °C
	Zone 3 temperature 第三段温度	215 °C
	Zone 4 temperature 第四段温度	210 °C
	Processing temperature 加工温度	240 ~ 260 °C
	Mold temperature 模具温度	80 ~ 120 °C
Pressure 压力	Back pressure 背压	0.294 ~ 0.686 MPa
Speed 速度	Screw Speed 螺杆转速	50 ~ 100 rpm

\* The data listed here is not for specification warranty, but typical value.

All products purchased from or supplied by Juhong Corporation are subject to terms and conditions set out in the contract, order acknowledgement and/or bill of lading. Values given above are simply references for representing typical level and do not expressly or impliedly guarantee anything. Neither should it be interpreted as specification limit nor sole criterion for part/tool design that is intended to have a legal binding effect. All other information, including that herein, supplied by Juhong is considered accurate but is furnished upon the express condition that the customer shall make its own assessment to determine the product's suitability for a particular purpose. Juhong makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent. Any references in this brochure to "Juhong" refer to the collectivity of Juhong engaged in the manufacture and sale of chemical products. Particular contracts are entered into by any such company individually and any warranty, representation or any other commitment provided by Juhong is the commitment of such individual company only.