




Beta Analytic Inc.
4985 SW 74 Court
Miami, Florida 33155 USA
Tel: 305-667-5167
Fax: 305-663-0964
info@betalabservices.com
www.betalabservices.com

Report of Biobased Content Analysis using ASTM-D6866

Submitter: ARKEMA
Submitter Label: Rilsan® Clear G830 Rnew
Laboratory Number: Beta-245730
Material Analyzed: BIOBASED SOLID
Date Received: June 20, 2008
Date Reported: June 24, 2008

Mean Biobased Result: 54% *

Proportions Biobased vs. Fossil Based
indicated by ^{14}C content



* ASTM-D6866 cites precision on The Mean Biobased Result as +/- 3% (absolute). This is the most conservative estimate of error in the measurement of complex biobased containing solids and liquids based on empirical results. Real precision for readily combustible and homogenous materials (e.g. gasoline) and especially samples received as CO₂ (e.g. flue gas or CEMS exhaust) can be as low as +/- 0.5-2%. The result only applies to the analyzed material. Fluctuations in carbon content within a batch of product, gasoline or flue gas must be determined separately (e.g. averaged measurements of multiple solids or liquids, and single measurement of the combination of gas aliquots collected over time). The accuracy of the result as it applies to the analyzed product, fuel, or flue gas relies upon all the carbon in the analyzed material originating from either recently respired atmospheric carbon dioxide (within the last few decades) or fossil carbon (more than 50,000 years old). "Percent biobased" specifically relates % renewable (or fossil) carbon to total carbon, not to total mass or molecular weight. Mean Biobased estimates greater than 100% are assigned a value of 100% for simplification.