

Durethan AM 230 H2.0 901510

PA 66, injection molding grade, 30% mineral, isotropic properties, heat-ageing stabilized

ISO Shortname: ISO 1874-PA 66,MHR,14-050,MD30

Property	Test Condition	Unit	Standard	Value	
				d.a.m.	cond.
Rheological properties					
Molding shrinkage, parallel	150x105x3; 280 °C / MT 80 °C; 500 bar	%	acc. ISO 2577	1.43	
Molding shrinkage, normal	150x105x3; 280 °C / MT 80 °C; 500 bar	%	acc. ISO 2577	1.44	
Post- shrinkage, parallel	150x105x3; 120 °C; 4 h	%	acc. ISO 2577	0.22	
Post- shrinkage, normal	150x105x3; 120 °C; 4 h	%	acc. ISO 2577	0.12	
Mechanical properties (23 °C/50 % r. h.)					
C Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	5100	2300
C Tensile Stress at break	5 mm/min	MPa	ISO 527-1,-2	90	60
C Tensile Strain at break	5 mm/min	%	ISO 527-1,-2	5.0	20
C Charpy impact strength	23 °C	kJ/m ²	ISO 179-1eU	100	N
C Charpy impact strength	-30 °C	kJ/m ²	ISO 179-1eU	70	70
C Charpy notched impact strength	23 °C	kJ/m ²	ISO 179-1eA	< 10	< 10
C Charpy notched impact strength	-30 °C	kJ/m ²	ISO 179-1eA	< 10	< 10
Charpy notched impact strength	-40 °C	kJ/m ²	ISO 179-1eA	< 10	< 10
Izod impact strength	23 °C	kJ/m ²	ISO 180-1U	130	N
Izod impact strength	-30 °C	kJ/m ²	ISO 180-1U	100	80
Izod notched impact strength	23 °C	kJ/m ²	ISO 180-1A	< 10	< 10
Izod notched impact strength	-30 °C	kJ/m ²	ISO 180-1A	< 10	< 10
Flexural modulus	2 mm/min	MPa	ISO 178	5000	2300
Flexural strength	2 mm/min	MPa	ISO 178	155	75
Flexural strain at flexural strength	2 mm/min	%	ISO 178	6.0	8.0
Flexural stress at 3.5 % strain	2 mm/min	MPa	ISO 178	140	60
C Puncture maximum force	23 °C	N	ISO 6603-2	2225	
C Puncture maximum force	-30 °C	N	ISO 6603-2	786	
C Puncture energy	23 °C	J	ISO 6603-2	4.5	
C Puncture energy	-30 °C	J	ISO 6603-2	0.8	
Ball indentation hardness		N/mm ²	ISO 2039-1	200	100
Thermal properties					
C Melting temperature	10 °C/min	°C	ISO 11357-1,-3	263	
C Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	~100	
C Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	~230	
C Temperature of deflection under load	8.00 MPa	°C	ISO 75-1,-2	~55	
Vicat softening temperature	50 N; 120 °C/h	°C	ISO 306	> 230	
C Coefficient of linear thermal expansion, parallel	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.6	
C Coefficient of linear thermal expansion, transverse	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.8	
C Burning behavior UL 94 (1.6 mm)	1.6 mm	Class	UL 94	HB*	



Durethan AM 230 H2.0 901510

Property	Test Condition	Unit	Standard	Value	
				d.a.m.	cond.
C Burning behavior UL 94	3.2 mm	Class	UL 94	HB*	
C Oxygen index	Method A	%	ISO 4589-2	26	
Glow wire test (GWFI)	2.0 mm	°C	IEC 60695-2-12	650	
Burning rate (US-FMVSS)	>=1.0 mm	mm/min	ISO 3795	passed	
C Vicat softening temperature	50 N; 50 °C/h	°C	ISO 306	> 230	
Electrical properties (23 °C/50 % r. h.)					
C Relative permittivity	100 Hz	-	IEC 60250	4.2	11
C Relative permittivity	1 MHz	-	IEC 60250	3.8	4.4
C Dissipation factor	100 Hz	10 ⁻⁴	IEC 60250	100	2250
C Dissipation factor	1 MHz	10 ⁻⁴	IEC 60250	170	750
C Volume resistivity		Ohm·m	IEC 60093	1E13	1E09
C Surface resistivity		Ohm	IEC 60093	1E14	1E12
C Electric strength	1 mm	kV/mm	IEC 60243-1	30	30
C Comparative tracking index CTI	Solution A	Rating	IEC 60112	575	
Comparative tracking index CTI M	Solution B	Rating	IEC 60112	425 M	
Other properties (23 °C)					
C Water absorption (Saturation value)	Water at 23 °C	%	ISO 62	~5.5	
C Water absorption (Equilibrium value)	23 °C; 50 % RH	%	ISO 62	~2.0	
C Density		kg/m ³	ISO 1183	1360	
Glass fiber / glass bead / filler content		%	ISO 3451-1	30	
Bulk density		kg/m ³	ISO 60	~700	
Processing conditions for test specimens					
C Injection molding-Melt temperature		°C	ISO 294	290	
C Injection molding-Mold temperature		°C	ISO 294	80	

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.



Durethan AM 230 H2.0 901510

Disclaimer

Disclaimer for sales products

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold and our advisory service is given in accordance with the current version of our General Conditions of Sale and Delivery.

Test values

Unless specified to the contrary, the values given have been established on standardized test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and the colouring.

Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.

LANXESS DEUTSCHLAND GMBH | D - 51369 LEVERKUSEN

© LANXESS Deutschland GmbH

